

Hole ID	Collar Easting	Collar Northing	Collar RL	Collar Dip	Collar Azimuth	Block	From (m)	To (m)	Downhole Interval (m)	Au Grade (g/t)	Grade x Downhole Interval (gm/t)	ETT* (m)	Cutoff** (Au g/t)
OKWD23-221	273002	702153	83	-62	272	1	319.0	359.4	40.4	1.01	41	32.6	0.3
<i>inc</i>							329.0	332.9	3.9	3.18	12	3.1	1.5
<i>inc</i>							340.0	345.0	5.0	2.56	13	4.1	1.5
OKWD23-237A	272851	700760	76	-49	275	6	207.0	222.9	15.9	0.37	6		0.3
and							262.0	340.6	78.6	1.36	107		0.3
<i>inc</i>							298.0	301.0	3.0	2.93	9		1.5
<i>inc</i>							305.0	314.0	9.0	5.86	53		1.5
OKWD23-238	273271	701497	123	-56	268	4	639.5	681.0	41.5	1.26	52	36.5	0.3
<i>inc</i>							671.3	678.0	6.7	5.56	37	5.9	1.5
and							694.0	707.2	13.2	0.41	5	11.7	0.3
OKWD23-239	273060	701798	80	-67	268	4	349.0	367.0	18.0	0.49	9	13.5	0.3
and							378.0	392.0	14.0	0.34	5	10.5	0.3
and							398.0	413.5	15.5	0.35	5	11.8	0.3
and							426.0	483.0	57.0	2.77	158	43.5	0.3
<i>inc</i>							434.5	441.5	7.0	3.97	28	5.3	1.5
<i>inc</i>							452.8	460.9	8.1	3.16	26	6.2	1.5
<i>inc</i>							469.7	476.0	6.4	13.12	83	4.9	1.5
OKWD23-241	272787	700357	77	-60	270	6	300.6	316.7	16.1	0.36	6		0.3
OKWD23-242	273165	701398	78	-61	272	4	557.3	582.1	24.9	1.29	32	22.4	0.3
<i>inc</i>							559.4	565.8	6.4	2.98	19	5.7	1.5
OKWD23-244	273192	701682	106	-69	274	4	585.2	701.0	115.8	1.89	219	89.3	0.3
<i>inc</i>							591.4	604.0	12.6	3.95	50	9.6	1.5
<i>inc</i>							614.0	637.2	23.2	5.36	124	17.8	1.5
<i>inc</i>							641.0	644.0	3.0	2.44	7	2.3	1.5
OKWD23-245	273272	701498	123	-63	280	4	670.2	695.0	24.8	0.62	15	20.6	0.3
and							713.0	728.0	15.0	2.95	44	12.8	0.3
<i>inc</i>							721.0	728.0	7.0	6.02	42	6.0	1.5
and							742.0	755.0	13.0	0.90	12	11.2	0.3
OKWD23-246	272848	700560	74	-50	272	6	316.6	329.7	13.1	0.78	10		0.3
OKWD23-247	273049	701879	79	-61	276	4	297.5	322.0	24.5	0.37	9	19.2	0.3
and							388.0	433.0	45.0	1.80	81	35.2	0.3
<i>inc</i>							389.0	392.0	3.0	4.03	12	2.3	1.5
<i>inc</i>							418.6	425.3	6.7	6.13	41	5.3	1.5
OKWD23-248	272702	701030	74	-53	266	5	0.0	19.0	19.0	0.46	9		0.3
and							93.2	127.6	34.4	0.83	29		0.3
<i>inc</i>							101.2	106.2	5.0	2.70	13		1.5
OKWD23-249	273128	701972	76	-60	282	4	359.0	369.3	10.3	0.70	7	8.7	0.3
and							422.6	438.2	15.7	2.62	41	13.4	0.3
and							457.8	505.0	47.2	0.50	24	40.7	0.3
OKWD23-250	273086	701639	90	-60	262	4	402.6	499.1	96.5	1.38	133	80.1	0.3
<i>inc</i>							406.1	411.0	4.9	2.52	12	4.0	1.5
<i>inc</i>							426.9	430.0	3.1	2.71	8	2.6	1.5
<i>inc</i>							437.1	441.1	4.0	5.54	22	3.3	1.5
<i>inc</i>							449.1	452.2	3.1	3.15	10	2.6	1.5
<i>inc</i>							460.6	464.5	3.9	4.27	17	3.3	1.5
<i>inc</i>							467.0	479.2	12.2	2.13	26	10.1	1.5
OKWD23-251	273113	702041	77	-70	275	1	495.0	530.0	35.0	1.31	46	27.1	0.3
<i>inc</i>							506.0	518.0	12.0	1.87	22	9.3	1.5
OKWD23-252	273036	702198	80	-58	281	1	340.7	359.0	18.4	1.00	18	15.6	0.3
OKWD23-253	272801	701165	85	-50	258	5	174.5	222.0	47.5	1.28	61		0.3
<i>inc</i>							180.0	183.0	3.0	9.25	28		1.5
<i>inc</i>							212.0	215.0	3.0	3.96	12		1.5
OKWD23-254	273041	701831	80	-52	261	4	262.4	383.1	120.7	3.13	377	108.3	0.3
<i>inc</i>							303.3	311.7	8.4	9.66	81	7.5	1.5
<i>inc</i>							346.9	382.0	35.2	7.42	261	31.7	1.5
OKWD23-255	273127	701972	76	-70	280	4	519.5	582.0	62.5	0.59	37	43.8	0.3
OKWD23-256	272803	701166	85	-65	270	5	104.0	116.0	12.0	0.67	8		0.3
and							200.0	250.0	50.0	0.95	47		0.3
OKWD23-257	273113	702040	77	-61	274	1	360.0	377.0	17.0	0.72	12	14.0	0.3
<i>inc</i>							362.0	365.0	3.0	2.99	9	2.5	1.5
and							396.0	469.8	73.8	0.95	70	61.6	0.3
<i>inc</i>							413.0	420.0	7.0	3.84	27	5.8	1.5
OKWD23-258	273086	701639	90	-60	276	4	383.0	479.5	96.5	1.89	182	83.0	0.3

Hole ID	Collar Easting	Collar Northing	Collar RL	Collar Dip	Collar Azimuth	Block	From (m)	To (m)	Downhole Interval (m)	Au Grade (g/t)	Grade x Downhole Interval (gm/t)	ETT* (m)	Cutoff** (Au g/t)
<i>inc</i>							410.0	415.1	5.1	3.02	15	4.4	1.5
<i>inc</i>							423.0	426.0	3.0	1.56	5	2.6	1.5
<i>inc</i>							444.0	447.2	3.2	9.66	31	2.8	1.5
<i>inc</i>							449.4	470.9	21.5	4.76	102	18.5	1.5
OKWD23-259	273042	701831	80	-57	262	4	260.8	340.7	79.9	0.87	69	67.7	0.3
<i>inc</i>							283.2	286.3	3.1	2.71	8	2.6	1.5
<i>inc</i>							319.3	328.5	9.2	3.08	28	7.7	1.5
and							351.1	403.8	52.7	4.55	240	44.8	0.3
<i>inc</i>							366.4	374.1	7.7	14.55	112	6.6	1.5
<i>inc</i>							381.2	402.8	21.6	5.40	116	18.3	1.5
OKWD23-260	272682	700974	73	-45	275	6	0.0	15.6	15.6	0.40	6		0.3
and							71.0	97.0	26.0	0.96	25		0.3
<i>inc</i>							91.0	94.0	3.0	3.85	12		1.5
OKWD23-261	273112	702041	77	-57	260	1	361.0	384.0	23.0	0.72	17	20.3	0.3
and							404.4	444.3	39.9	0.76	30	35.7	0.3
<i>inc</i>							413.0	417.0	4.0	1.94	8	3.6	1.5
OKWD23-262	272839	702729	74	-50	240	1	7.5	19.0	11.5	0.45	5	9.2	0.3
and							62.0	79.0	17.0	0.35	6	13.5	0.3
OKWD23-263	273068	701801	78	-60	277	4	355.0	371.7	16.7	1.36	23	14.1	0.3
and							383.4	436.7	53.3	2.85	152	45.6	0.3
<i>inc</i>							394.7	404.3	9.7	3.48	34	8.2	1.5
<i>inc</i>							407.3	417.0	9.8	8.65	84	8.3	1.5
<i>inc</i>							428.0	431.6	3.6	4.18	15	3.1	1.5
OKWD23-264	272656	700734	86	-51	256	6	20.0	39.0	19.0	0.33	6		0.3
and							81.0	142.0	61.0	0.95	58		0.3
<i>inc</i>							89.0	101.0	12.0	1.82	22		1.5
<i>inc</i>							126.5	133.0	6.5	2.95	19		1.5
OKWD23-265	272720	702504	87	-65	270	1	18.0	32.0	14.0	0.33	5	10.5	0.3
OKWD23-266	273091	702108	75	-53	262	1	360.8	379.0	18.2	0.76	14	16.2	0.3
OKWD23-267	272798	702543	70	-50	270	1	120.0	124.0	4.0	2.66	11	3.7	1.5
OKWD23-268	273086	701639	90	-72	266	4	456.2	472.2	16.1	1.21	19	11.5	0.3
and							486.0	556.0	70.0	2.44	171	50.9	0.3
<i>inc</i>							498.0	503.0	5.0	6.56	33	3.6	1.5
<i>inc</i>							509.6	528.0	18.4	5.88	108	13.4	1.5
<i>inc</i>							534.0	538.0	4.0	2.03	8	2.9	1.5
OKWD23-269	273099	701551	111	-63	273	4	455.4	529.0	73.6	1.76	130	60.7	0.3
<i>inc</i>							479.3	482.5	3.2	1.75	6	2.6	1.5
<i>inc</i>							496.4	507.0	10.6	5.59	59	8.8	1.5
<i>inc</i>							521.0	524.5	3.5	6.14	22	2.9	1.5
OKWD23-271	272984	701717	79	-57	280	4	224.5	339.0	114.5	2.02	232	99.0	0.3
<i>inc</i>							265.5	271.6	6.2	1.59	10	5.3	1.5
<i>inc</i>							307.3	329.6	22.3	4.43	99	19.5	1.5
<i>inc</i>							333.0	336.0	3.0	2.74	8	2.6	1.5
OKWD23-273	273035	702124	78	-53	276	1	277.0	298.0	21.0	0.30	6	19.0	0.3
and							326.0	360.0	34.0	0.81	28	30.9	0.3
<i>inc</i>							327.0	331.0	4.0	1.67	7	3.6	1.5
OKWR23-1006	269090	702780	124	-60	270	0	14.0	31.0	17.0	1.71	29		0.3
<i>inc</i>							14.0	19.0	5.0	4.08	20		1.5

* Estimated True Thickness ("ETT") based on an average dip / dip direction of -65° / 095° to represent the orientation of the mineralized zone in Block 4. ETT only calculated for Blocks 1 and 4.

** Significant intervals calculated using a 0.3 g/t Au cutoff, 10m minimum length and 10m maximum consecutive internal waste. Included intervals calculated using a 1.5 g/t Au cutoff, 3m minimum length and a 2m maximum consecutive internal waste.